

### Nickel Alloy

### Alloy 690

### (UNS N06690)

#### Application

Alloy 690 is a high-chromium nickel alloy having excellent resistance to many corrosive aqueous media and hightemperature atmospheres. The alloy's high chromium content gives it excellent resistance to caturisation, metal dusting, oxidation and sulfidation at high temperature. In addition to its corrosion resistance, alloy 690 has high strength, good metallurgical stability, and favorable fabrication characteristics.

#### Available tube product forms

STRAIGHT || SEAMLESS ||

#### Typical manufacturing specifications

ASTM B167

Also individual customer specifications.

#### Industries predominantly using this grade

Oil and gas, Chemical processes,  
 Nuclear and power etc.

#### Technical Data

#### Chemical composition(% by weight)

Element	Ni	Cr	Fe	Mn	C	Cu	Si	S	-	-	-	-
Minimum	58.0	27.0	7.0	-	-	-	-	-	-	-	-	-
Maximum	-	31.0	11.0	0.5	0.05	0.5	0.5	0.015	-	-	-	-

#### Mechanical Properties

	Tubing, Annealed (OD 5 in. under)		Tubing, Annealed (Over OD 5 in.)	
Tensile Rm	85	ksi (min.)	85	ksi (min.)
Tensile Rm	586	MPa (min.)	586	MPa (min.)
Yield (R.p. 0.2%)	35	ksi (min.)	30	ksi (min.)
Yield (R.p. 0.2%)	240	MPa (min.)	205	MPa (min.)
Elongation	30	% (min.)	35	% (min.)

#### Physical Properties(Room Temperature)

Specific Heat (0-100°C)	450	J.kg <sup>-1</sup> .°K <sup>-1</sup>
Thermal Conductivity	13.5	W.m <sup>-1</sup> .°K <sup>-1</sup>
Thermal Expansion	14	µm/m.°C
Modulus Elasticity	211	GPa
Electrical Resistivity	115	µohm.cm
Density	8.2	g/cm3

#### Microstructure



#### Maximum allowable pressure (Unit : BAR)

		Wall thickness (mm)						
		0.89	1.24	1.65	2.11	2.77	3.96	4.78
Outside diameter (mm)	6.35	451	655	897	1197	-	-	-
	9.53	290	415	572	780	1011	-	-
	12.7	213	304	414	566	741	-	-
	19.05	-	197	267	361	470	-	-
	25.4	-	146	197	265	342	508	629
	31.8	-	-	156	209	269	396	487
	38.1	-	-	129	173	222	325	399
	50.8	-	-	96	128	164	239	292

\* Please let us know your design pressure, we can produce requested tube size

\* The table above is for your reference